

SONOLASTIC® NP 2™

Multiple-component high-performance polyurethane sealant

PRODUCT DATA

7 07920

Joint Sealants

Description

NP 2™ is a three-component, highly flexible, nonpriming, high-performance polyurethane sealant. It has been successfully tested for joint movement of plus or minus 50%. Choose from 40 popular stock colors and 463 standard colors.

Yield

See page 3 for charts.

Packaging

1-1/2 gallon units in 2 gallon (5.67 L) pails

3 gallon unit in 3-1/2 gallon (11.3 L) pails

Available in pretinted colors: Precast Gray and Limestone

1-1/2 gallon units in 2 gallon (5.67 L) pails

3 gallon units in 3-1/2 gallon (11.3 L) pails

Colors

40 standard, stocked colors are available. Refer to the Popular Palette for Sealants and Waterproofing.

463 standard (nonstocked) colors are also available, and custom matching can be done upon request. Refer to the Sonneborn® Color Portfolio.

Shelf Life

1 year when properly stored

Features

- Elastomeric, movement capability of ±50%
- Resistant to weather, airborne pollutants, and chemicals
- Superior adhesion
- NP 2™ accelerator available
- Sonneborn® Color Portfolio available
- Excellent gunability over a broad temperature range
- Nonstaining
- UL listed

Storage

Store in unopened containers in a cool, clean, dry area. Do not open containers until ready for use.

Where to Use

APPLICATION

- Expansion joints
- Curtain walls
- Panel walls
- Precast units
- Perimeter window caulking
- EIFS
- Tilt-up panel joints
- Vinyl siding
- Parking decks

LOCATION

- Horizontal and vertical joints
- Interior and exterior

Benefits

- Adds protection against unanticipated movement
- Long-lasting performance on all applications
- Requires no primer on many construction materials
- Use for cold climate applications; speeds initial cure
- Choose from 463 custom colors
- Speeds application
- Use where aesthetics are a primary concern
- Passes 4 hour, 4 inch, fire and hose stream test when used with Ultra Block®

SUBSTRATE

- Concrete
- Masonry
- Aluminum
- Marble
- Granite
- Brick
- Stucco
- Limestone

How to Apply

Joint Preparation

1. The number of joints and the joint width should be designed for a maximum of ±25% movement.
2. The depth of the sealant should be one-half the width of the joint. The maximum depth is 1/2" (13 mm) and the minimum is 1/4" (6 mm) Maximum recommended joint width is 2". Refer to Table 1 on next page.



Technical Data

Composition

NP 2™ is a three-component polyurethane product.

Compliances

- ASTM C 920, Type M, Grade NS, Class 25, use NT, T, G, A, M, and O
- Federal Specification TT-S-00227E, Type II, Class A
- Corps of Engineers CRD-C-506
- Canadian Standards Board CAN/CGSB-19.24-M90, Classification MCG-2-40-A-N, No. 81029
- Canadian approval for use in establishments that handle food
- USDA compliant for use in meat and poultry areas
- Underwriters Laboratories Inc.® classified (fire resistance only).

Typical Properties

PROPERTY	VALUE
Temperature range, ° F (° C)	-40 to 180 (-40 to 82)
Expected life	Up to 15 years
Shrinkage	None

Test Data

PROPERTY	RESULTS	TEST METHODS
Tensile strength, psi (MPa)	160 (1.1)	ASTM D 412
Ultimate elongation at break, %	280	ASTM D 412
Stain and color change	Passes (no visible stain)	ASTM C 510
Extrusion rate, sec, 3 hrs after mixing	6 Passes	ASTM C 603
Rheological (flow), at 120° F (49° C)	Nonsag	ASTM C 639
Hardness, Shore A		ASTM C 661
At standard conditions	25	
After heat aging (max Shore A:50)	22	
Tack-free time, hrs, (maximum 72 hrs)	< 48 hours	ASTM C 679
Bond durability*, %, on glass, aluminum, and concrete	±25	ASTM C 719
Weight loss, after heat aging, %	4.7	ASTM C 792
Cracking and chalking, after heat aging	None	ASTM C 792
Artificial weathering, Xenon arc, 250 hours	Passes	ASTM C 793
Artificial weathering, Xenon arc, 2,000 hours	No surface cracking	ASTM G 26
Adhesion in peel, on glass, aluminum, and concrete*, pli	> 10	ASTM C 794
Adhesion in peel,* after UV radiation through glass, pli	> 10	ASTM C 794

* Primed for water immersion dictated by ASTM C 920. Concrete and aluminum primed with 733; glass primed with 766.

Test results are typical values obtained under laboratory conditions. Reasonable variations can be expected.

TABLE 1

Joint width and Sealant Depth

JOINT WIDTH, IN (MM)	SEALANT DEPTH AT MIDPOINT, IN (MM)
1/4 – 1/2 (6 – 13)	1/4 (6)
1/2 – 3/4 (13 – 19)	1/4 – 3/8 (6 – 10)
3/4 – 1 (19 – 25)	3/8 – 1/2 (10 – 13)
1 – 1-1/2 (25 – 38)	1/2 (13)

3. In deep joints, the sealant depth must be controlled by Closed-Cell Backer-Rod or Soft Backer-Rod (see Form No.1026342). Where the joint depth does not permit the use of backer-rod, a bondbreaker (polyethylene strip) must be used to prevent three-sided adhesion. For horizontal joints, use Closed Cell Backer Rod.

4. To maintain the recommended sealant depth, install backer-rod by compressing and rolling it into the joint channel without stretching it lengthwise. Closed-Cell Backer-Rod should be about 1/8" (3 mm) larger in diameter than the width of the joint to allow for compression. Soft Backer-Rod should be approximately 25% larger in diameter than the joint

width. The sealant does not adhere to it, and no separate bondbreaker is required. Do not prime or puncture the backer-rod.

Surface Preparation

Surfaces must be structurally sound, fully cured, dry, clean, free of dirt, moisture, loose particles, oil, grease, asphalt, tar, paint, wax, rust, water-proofings, curing and parting compounds, and membrane materials.

CONCRETE, STONE, AND OTHER MASONRY

Clean by grinding, sandblasting, or wire brushing to expose a sound surface free of contamination and laitance.

Yield

LINEAR FEET PER GALLON*

JOINT DEPTH (INCHES)	JOINT WIDTH (INCHES)						
	1/4	3/8	1/2	5/8	3/4	7/8	1
1/4	308	205	154	122	—	—	—
3/8	—	—	82	68	58	51	—
1/2	—	—	—	—	51	44	38

METERS PER LITER

JOINT DEPTH (MM)	JOINT WIDTH (MM)						
	6	10	13	16	19	22	25
6	24.8	16.5	12.4	9.8	—	—	—
10	—	—	—	6.6	5.5	4.7	4.1
13	—	—	—	—	4.1	3.5	3.0

WOOD

New and weathered wood must be clean and sound. Scrape away loose paint to bare wood. Any coating that cannot be removed must be tested to verify adhesion of sealant or determine an appropriate primer.

METAL

Remove scale, rust, and coatings from metal to expose a bright white surface. Remove protective coatings as well as any chemical residue or film. Aluminum window frames are frequently coated with a clear lacquer that must be removed before the application of NP 2™. Any coating that cannot be removed must be tested to verify adhesion of sealant or determine an appropriate primer. Remove any other protective coatings or finishes that could interfere with adhesion.

Priming

1. NP 2™ is generally considered a non-priming sealant, but special circumstances or substrates may require a primer. It is the user's responsibility to check the adhesion of the cured sealant on typical test joints at the project site before and during application. Refer to product data sheet on Primer 733 or 766 (Form No. 1017962), and consult Technical Service for additional information.

2. Apply primer full strength with a brush or clean cloth. A light, uniform coating is sufficient for most surfaces. Porous surfaces require more primer; however, do not overapply.

3. Allow primer to dry before applying NP 2™. Depending on temperature and humidity, primer will be tack free in 15 – 120 minutes. Priming and sealing must be done on the same work day.

Mixing

1. NP 2™ is a three-component system and must be thoroughly mixed before use. The oversize Part A container allows for the addition and mixing of Part B and Sonolastic® color pigment into Part A.

2. 1-1/2 gallon (5.67 L) unit: Transfer entire contents of Part B to Part A container using a spatula or a margin trowel.

3. It is imperative that Part B be mixed thoroughly with Part A. Before adding Sonolastic® pigment, scrape sides of container to ensure complete mixing of Parts A and B.

4. With a slow-speed drill and a sealant mixing paddle, mix 4 – 6 minutes. The paddle blade must be kept below the surface of the sealant to avoid whipping air into the sealant.

5. Transfer the entire contents of the Sonolastic® pigment can into the mixed Part A and B. Use a spatula or knife to remove all the pigment from the container. Continue mixing with a slow-speed (500 – 600 rpm) drill and slotted paddle until color is uniform. During the process, the sides and bottom of the container must be scraped several times to obtain a complete mix.

6. 3 gallon (11.37 L) unit: Use 2 Part B and 2 Sonolastic® pigment containers for each Part A container. Mix as instructed under 1-1/2 gallon (5.7 L) unit.

7. The pot life of mixed NP 2™ is influenced by temperature. See Table 2 for specific data. NP 2™ accelerator or extender may be added to adjust the initial cure rate.

TABLE 2

Working Times, hours

	Standard conditions 73° F (3° C) 0% rh	Higher temperature 95° F (35° C), 5 – 90% rh	Colder temperature 40° F (4° C)
No accelerator	2 – 3	1 – 2	4 – 6
1 accelerator	1 – 2	< 1	2 – 3
2 accelerators	< 1	—	1.5 – 2.5

Application

1. Except when unusual job conditions dictate the use of knife or spatula, apply NP 2™ by professional bulk gun loaded at the jobsite. Fill joints from the bottom up to the exterior face by holding a properly sized nozzle against the joint bottom.
2. Proper tooling ensures the correct bead configuration and a neat joint. Equally important, it ensures maximum adhesion to the sides of the joint. For best results, dry tool. DO NOT use water or soapy water to tool. Avoid overtooling of sealant.
3. Best practices dictate that all caulking and sealing be done when temperatures are above 40° F (4° C) to avoid application to moisture-laden surfaces. Moisture on substrates will adversely affect adhesion.
4. Application may proceed as low as 20° F (-6° C) if there is certainty that substrates are completely dry, free of moisture, and clean as described under Surface Preparation.

Clean Up

Immediately after use and before sealant has cured, clean equipment with Reducer 990 or xylene. Cured sealant may be removed by cutting with a sharp-edged tool; thin films by abrading.

Curing

1. NP 2™ cures by a chemically controlled reaction. Initial cure is within 24 hours, and complete cure takes approximately 7 days. Cure rates are dependent on temperature and humidity.
2. The initial cure rate of NP 2™ can be adjusted for seasonal and geographic climactic conditions. See Table 2 for use of accelerator and extender.

For Best Performance

- Do not allow uncured NP 2™ to come into contact with alcohol-based materials or solvents.
- Do not apply polyurethane sealants in the vicinity of uncured silicone sealants or uncured Sonolastic® 150 with VLM Technology or 150 Tint Base.
- NP 2™ should not come in contact with oil-based caulking, silicone sealants, polysulfides, or fillers impregnated with oil, asphalt, or tar.
- Do not apply epoxy-based coatings in the vicinity of uncured NP 2™.
- Do not apply to freshly treated wood; treated wood must have weathered for at least 6 months.
- Do not open containers until ready for use.
- Units are premeasured; do not use partial units.
- NP 2™ may yellow in the presence of unvented artificial heat; this is a surface phenomenon that does not affect sealant performance.
- NP 2™ should not be used for continuous immersion in water. Call Technical Service for recommendations.
- Horizontal joints subject to traffic or intermittent ponding of water require the use of primer. Call Technical Service for details
- Substrates such as copper, stainless, and galvanized typically require the use of a primer; Primers 733 or 766 are acceptable. For Kynar coating use Primer 733 only. An adhesion test is recommended for any other questionable substrate.
- Do not use as a cap, heel, or toe bead for exterior glazing. Refer to Sonolastic® 150 product data guide (Form No. 1026309).
- Use only color packs designed for use with NP 2™.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by Degussa personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

NP 2™ PART A

Warning

NP 2™ Part A contains mineral spirits, calcium carbonate, toluene diisocyanate, 1, 2, 4 trimethyl benzene, naphtha-light aromatic, titanium dioxide, and crystalline silica.

Risks

May cause skin and eye irritation. May cause dermatitis and allergic responses. Potential skin and/or respiratory sensitizer. Inhalation may cause irritation and intoxication with headaches, dizziness and nausea. Ingestion may cause irritation. Reports associate repeated or prolonged occupational overexposure to solvents with damage to brain, nervous system, liver or kidneys. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

Precautions

KEEP OUT OF THE REACH OF CHILDREN. Prevent contact with skin, eyes and clothing. Wash thoroughly after handling. Use only with adequate ventilation. Keep container closed when not in use. DO NOT take internally. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations. Empty container may contain hazardous residues. All label warnings must be observed until container is commercially cleaned or reconditioned.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product contains materials listed by the state of California as known to cause cancer, birth defects, or other reproductive harm.

VOC Content

0.44 - 0.67 lbs/gal or 53 - 80 g/L, less water and exempt solvents.

NP 2™ PART B

Warning

NP 2™ Part B contains toluene diisocyanate mix.

Risks

May cause skin, eye, or respiratory irritation. May cause dermatitis and allergic reactions. Potential skin and respiratory sensitizer. Ingestion may cause irritation.

Precautions

KEEP OUT OF THE REACH OF CHILDREN. Prevent contact with skin, eyes, and clothing. Wash thoroughly after handling. DO NOT take internally. Ingestion may cause irritation. Use only with adequate ventilation. Inhalation may cause irritation. Keep container closed. Use impervious gloves, eye protection, and if the TLV is exceeded or if used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state, and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product contains materials which are known to the state of California as known to cause cancer, birth defects, or other reproductive harm.

VOC Content

0.07 lbs/gal or 8.09 g/L, less water and exempt solvents.

NP 2™ ACCELERATOR

Warning

NP 2™ Accelerator contains mineral oil, and 2-ethylhexanoic acid.

Risks

May cause skin, eye or respiratory irritation. May be absorbed through the skin. May cause dermatitis and allergic reactions. Ingestion may cause irritation. Repeated or prolonged absorption may affect the kidneys.

Precautions

KEEP OUT OF THE REACH OF CHILDREN. Prevent contact with skin, eyes and clothing. Wash thoroughly after handling. DO NOT take internally. Use only with adequate ventilation. Inhalation may cause irritation. Keep container closed. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product does not knowingly contain materials which are known to the state of California as known to cause cancer, birth defects, or other reproductive harm.

VOC Content

0 lbs/gal or 0 g/L, less water and exempt solvents.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

Degussa Building Systems

889 Valley Park Drive
Shakopee, MN, 55379

www.degussabuildingsystems.com

Customer Service 800-433-9517
Technical Service 800-243-6739

LIMITED WARRANTY NOTICE Every reasonable effort is made to apply Degussa exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, Degussa MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and Degussa shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the Degussa Technical Manager.

This information and all further technical advice are based on Degussa's present knowledge and experience. However, Degussa assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, Degussa disclaims all WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. DEGUSSA SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. Degussa reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1017911 9/03 (Replaces 1/02)
Printed on recycled paper including 10% post-consumer fiber.

© 2003 Degussa
Printed in U.S.A.